



ICRC/IFRC STANDARD

CUSTOMER REFERENCE

HSHEBLANPMT1

05787

DESCRIPTION

- » Knitted blanket dry raised on both sides
- » 2 fold fleece layers in 100% virgin polyester
- » Min. 400 gsm - max. 700 gsm

MAIN MATERIALS

| | |
|-----------------------|--|
| MATERIAL | 100% virgin polyester on dry weight as per ISO 1833 |
| TENSILE STRENGTH | Min. 250 N warp and weft as per ISO 13934-1 |
| TENSILE STRENGTH LOSS | Less than 5% after washing as per ISO 6330 & ISO 13934-1 |
| THICKNESS | Min 6,5mm as per ISO 5084 (1KPA on 2000 mm ²) |
| SHRINKAGE | Less than 5% after washing as per ISO 6330 |
| WEIGHT LOSS | Less than 5% after washing as per ISO 6330 |
| TOG | Min. 2,5 RCT (= 2,5 TOG) |
| RESISTANCE TO AIRFLOW | Less than 1000 L/m ² /s as per ISO 9237 under 100 Pa pressure drop |
| FINISH | Seam of 10 to 13 stitches per 10 cm |
| ORGANOLEPTIC TEST | No bad smell, not irritating, no dust, PH between 4 and 9, fit for human use and free from harmful VOC |
| FLAME RESISTANCE | Flame proof as per ISO 12952-2 |
| CIGARETTE RESISTANCE | Cigarette proof as per ISO 12952-1 |
| COLOR | Grey shade blanket |

DIMENSIONS

| | |
|----------------|---------------------------|
| LENGTH x WIDTH | 150 x 200 cm ± 1% |
| WEIGHT | Min. 400 g - max. 700 gsm |

PACKING

| | |
|---|--|
| PACKING UNIT (P.U.) | Bale |
| QTY P.U. | 20 pcs per bale |
| P.U. MEASUREMENTS | DIMENSIONS: 78 x 52 x 56 cm WEIGHT: 25,5 kg VOLUME: 0,23 m ³ |
| QTY PALLET | 4 or 8 bales per CRI pallet |
| PALLET MEASUREMENTS 4 BALES PER PALLET | DIMENSIONS: 115 x 75 x 125 cm WEIGHT: 117 kg VOLUME: 1,08 m ³ |
| PALLET MEASUREMENTS 8 BALES PER PALLET | DIMENSIONS: 115 x 75 x 210 cm WEIGHT: 219 kg VOLUME: 1,81 m ³ |
| LOADING | PER 20 FT DC 2460 pcs unpalletized 2240 pcs palletized PER 40 FT HC 6000 pcs unpalletized 4800 pcs palletized |

INDICATED WEIGHTS AND VOLUMES ARE FOR YOUR INFORMATION ONLY AND MAY VARY ACCORDING TO PRODUCT SPECIFICATION.
FOR ALL DIMENSIONS AND WEIGHTS A TOLERANCE OF 3% IS APPLIED

Specifications & design may be altered without notice due to continuous product development.
LAST UPDATED 1/2026